

Safety Track® 3307

Issue Date: 1/17/2023 Version 1.1

DESCRIPTION

Jessup 3307 Safety Track® Crystal Clear is a virtually invisible 60 grit non-slip tape. This product is NSF “Slip Resistant” and meets OSHA, ADA standards for general purpose anti-slip surface applications.

APPLICATION & FEATURES

- Durability and UV protection up to 12 months
- Indoor/outdoor non-slip applications such as boating, motor cross, surfboards, stairs, ramps and more
- Barefoot and mop friendly

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC – 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.014 inch (0.330 mm) 0.001 inch (0.031 mm) 0.0065 inch (0.165 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15 minute dwell 24 hour dwell	60 oz/in (66 N/100 mm) 75 oz/in (83 N/100 mm)
- Powder coated surfaces *	15 minute dwell 24 hour dwell	25 oz/in (27 N/100 mm) 25 oz/in (27 N/100 mm)
- Polyethylene	15 minute dwell 24 hour dwell	55 oz/in (61 N/100 mm) 70 oz/in (77 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2" x 1/2" x 1000g	< 5 hours
Tack	PSTC - 6 Rolling Ball Tack	< 5 inches
Temperature Range		
- Application Temperature		>60°F
- Operating Temperature		-10 - 200°F

* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Coefficient of Friction (Kinetic)	ASTM D1894 -Dry Rubber -Wet Rubber -Dry Leather -Wet Leather	0.7 0.75 0.5 0.9
RATINGS & CERTIFICATIONS	DIN EN 16165:2023-02, Annex B	R11
COMPATIBLE INKS	UV	
CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed, and product is immediately tested for scrape resistances, delaminating, and other visual effects.)	Water 10% Saltwater Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Floor Cleaner All Purpose Cleaner 50% Antifreeze in water MEK Mineral Spirits 99% IPA	Recommended Recommended Recommended Not Recommended Intermittent Contact Only Recommended Intermittent contact only Recommended Recommended Recommended Not Recommended Recommended Recommended

Note: While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.

WARRANTY

The determination of the suitability of this product for any specific use is solely the responsibility of the user. No representations, guarantees or warranties of any kind are made to the accuracy or suitability of information in this document to any specific applications. Jessup warrants its products to be free from defects but limits its obligation to replacement of products that have been proven, to Jessup's satisfaction, to be defective. This warranty is non-transferable and only applies to customers buying directly from Jessup. Jessup is not liable for any loss, damage, expenses, or consequential damages arising in connection with the use of this product.