

TenaciousTac® WHT-PET-1CR

Issue Date: 5/8/2024 Version 1.2

DESCRIPTION

Printable 2 mil white PET with 1 mil of a chemically resistant, permanent acrylic adhesive.

APPLICATION & FEATURES

- Graphics
- Durable labels/decals
- Excellent adhesion to LSE surfaces
- Good for die cutting and sheeting

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC – 133 - Substrate - Pressure Sensitive Adhesive - Release Liner	0.0020 inch (0.0508 mm) 0.0010 inch (0.0254 mm) 0.0065 inch (0.1651 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15-minute dwell 24-hour dwell	70 oz/in (77 N/100 mm) 85 oz/in (93 N/100 mm)
- Powder coated surfaces *	15-minute dwell 24-hour dwell	65 oz/in (71 N/100 mm) 80 oz/in (88 N/100 mm)
- Polyethylene	15-minute dwell 24-hour dwell	50 oz/in (55 N/100 mm) 50 oz/in (55 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2" x 1/2" x 1000g	< 20 hours
Tack	PSTC – 6 Rolling Ball Tack	 10+ inches
Temperature Range		
- Application Temperature		>7°F
- Operating Temperature		-13 - 200°F

* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

PHYSICAL PROPERTIES	TEST	AVERAGE RESULTS
Compatible Inks	Solvent, offset, digital, laser jet, inkjet and UV	
CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<p><u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed, and product is immediately tested for scrape resistances, delaminating, and other visual effects.)</p>	Water 10% Saltwater Bleach Ammonia 25% Sulfuric Acid Detergent All Purpose Cleaner 99% IPA Glass cleaner Disinfectant	Recommended Recommended Recommended Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended

Note: While the data contained herein is believed to be reliable averages of the product’s properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.