

TenaciousTac® CLR-1CRAE

Issue Date: 5/8/2024 Version 1.1

DESCRIPTION

Printable 3.5 mil matte calendared clear vinyl coated with 1 mil of chemically resistant, permanent acrylic adhesive. This product utilizes an air egress liner for ease of installation.

APPLICATION & FEATURES

- Graphics
- Durable labels/decals
- 5 year weatherable
- Excellent adhesion to LSE surfaces
- Repositionable
- Compatible with all ink technologies

PROPERTIES

| PHYSICAL PROPERTIES | TEST METHODS | AVERAGE RESULTS |
|----------------------------|---|---|
| Thickness | PSTC – 133 - Substrate - Pressure Sensitive adhesive - Release Liner | 0.0035 inch (0.0889 mm) 0.0010 inch (0.0254 mm) 0.0070 inch (0.1778 mm) |
| Peel Adhesion to: | PSTC – 101 | |
| - Stainless Steel | 15-minute dwell 24-hour dwell | 65 oz/in (71 N/100 mm) 80 oz/in (88 N/100 mm) |
| - Powder coated surfaces * | 15-minute dwell 24-hour dwell | 60 oz/in (66 N/100 mm) 65 oz/in (71 N/100 mm) |
| - Polyethylene | 15-minute dwell 24-hour dwell | 45 oz/in (49 N/100 mm) 45 oz/in (49 N/100 mm) |
| Shear Adhesion to: | PSTC – 107 | |
| - Stainless Steel | 1/2" x 1/2" x 1000g | < 1 hours |
| Tack | PSTC - 6 Rolling Ball Tack | 10+ inches |
| Temperature Range | | |
| - Application Temperature | | >7°F |
| - Operating Temperature | | -13 - 200°F |

* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

| PHYSICAL PROPERTIES | TEST | AVERAGE RESULTS |
|---|--|--|
| Compatible Inks | All Ink Technologies | |
| CHEMICAL PROPERTIES | REAGENT | RECOMMENDATION |
| <p><u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed, and product is immediately tested for scrape resistances, delaminating, and other visual effects.)</p> | Water 10% Saltwater Bleach Ammonia 25% Sulfuric Acid Detergent All Purpose Cleaner 99% IPA Glass cleaner Disinfectant | Recommended Recommended Recommended Recommended Intermittent Contact Only Recommended Recommended Recommended Recommended Recommended |

Note: While the data contained herein is believed to be reliable averages of the product’s properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.