

Glo Brite® 7650

Issue Date: 11/14/2024 Version 1.7

DESCRIPTION

Jessup Glo Brite® 7650 is a high-performance safety grade flexible photoluminescent film coated with a permanent acrylic adhesive and has a matte HD print receptive surface layer. It has been designed to exceed requirements for life safety, emergency egress, and other safety standards.

APPLICATION & FEATURES

- Indoor, outdoor safety applications
- Target markets, fire safety and egress signage for buildings marine, rail, and military applications

PROPERTIES

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	PSTC – 133 - Substrate - Pressure Sensitive adhesive - Release Liner	0.009 inch (0.229 mm) 0.002 inch (0.051 mm) 0.006 inch (0.152 mm)
Peel Adhesion to:	PSTC – 101	
- Stainless Steel	15-minute dwell 24-hour dwell	96 oz/in (105 N/100 mm) 110 oz/in (120 N/100 mm)
- Powder coated surfaces *	15-minute dwell 24-hour dwell	80 oz/in (88 N/100 mm) 90 oz/in (100 N/100 mm)
- Polyethylene	15-minute dwell 24-hour dwell	70 oz/in (77 N/100 mm) 80 oz/in (88 N/100 mm)
Shear Adhesion to:	PSTC – 107	
- Stainless Steel	1/2" x 1/2" x 1000g	< 5 hours
Tack	PSTC - 6 Rolling Ball Tack	< 3 inches
Adhesive Temperature Range		
- Application Temperature		>0°F
- Operating Temperature		-10 - 375°F

* Color and lot variances of coated surfaces including paints, powder coatings, lacquers, stains, and other treatments may vary the performance of the tape and should be evaluated for the compatibility of the tape to the specific surface.

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Luminous Values	DIN 67510 / ASTM 2072 (Xe lamp 1000Lx / 5 min) 10 min (Xe lamp 1000Lx / 5 min) 60 min	150 mcd/m ² 23 mcd/m ² 1200 min to 0.3 mcd/m ²
Luminous Compliance	DIN 67510, ASTM 2072, ISO 15370, IMO RES A. 752 (18), PSPA class C, JIS Z9100, IBC, IFC, UL 1994 Listed, MED EU Marine Equipment Directive	
Compatible Inks	Solvent, UV inks and Thermal transfer systems	
CHEMICAL PROPERTIES	REAGENT	RECOMMENDATION
<p><u>Solvent Resistance</u> (Product laminated to stainless steel panel and allowed to condition for 24 hours at room temperature before testing. Sample was covered with reagent to the point that edges of product are also exposed to the reagent. The product is exposed to reagent for one hour at room temperature, then reagent is removed, and product is immediately tested for scrape resistances, delaminating, and other visual effects.)</p>	<p>Water 10% Salt Water Bleach Trichloroethylene 25% Sulfuric Acid 1% Sodium Hydroxide Unleaded Gasoline Diesel Fuel Hydraulic Fluid 50% Antifreeze in water MEK Mineral Spirits 99% IPA</p>	<p>Recommended Recommended Recommended Not Recommended Recommended Intermittent Contact Only Intermittent Contact Only Intermittent Contact Only Recommended Recommended Not Recommended Recommended Recommended</p>

Note: While the data contained herein is believed to be reliable averages of the product's properties, the data should not be used for specification purposes. Test Data and results contained in this document are for general guidance only and should not be used by customers to establish designs and specifications. Customers who desire specific performance data should contact Jessup Manufacturing Company for further recommendations.